

# HIGH-STRENGTH FINE-GRAINED WEAR RESISTANT STEEL

**SIDUR 550** is a high-strength fine-grained wear resistant steel. It is intended for use in components that require high resistance to abrasive sliding wear. Typically, the plates made of this steel are used as add-on plates in the areas with extreme wear providing prolonged component lifetime. Material can be welded in the final structures using the GMAW process.

## STANDARDS

- General technical delivery requirements in accordance with EN 10021.
- Tolerances on dimensions and shape according to EN 10029.
- Delivery requirements for surface condition according to EN 10163-2.
- Ultrasonic testing according to EN 10160.
- Tensile testing at room temperature according to EN ISO 6892-1.
- Impact testing according to EN ISO 148-1.
- Brinell hardness testing according to ISO 6506-1.

# CHEMICAL COMPOSITION

SIDUR 550	С	Si	Mn	Р	S	Cr	Mo	Ni	Ti	В
Max. in %	0.38	1.0	1.5	0.02	0.05	1.1	0.5	1.3	0.04	0.005

The steel contains grain-refining elements.

SIDUR 550	6–25 mm		
CEV* (max. in %)	0.78		
$*CEV = C + \frac{Mn}{6} + \frac{Cr + Mo + V}{5} + \frac{Ni + Cu}{15}$			

# MECHANICAL PROPERTIES

Thickness	Surface hardness*
[mm]	HB <sub>10/3000</sub>
6–25	510–580

\* One measurement per plate.

🛆 SIJ ACRONI d.o.o.

4270 Jesenice, Slovenija, EU 6 +386 4 58 41 000 ♣ +386 4 58 41 003
☑ uprava@acroni.si
⑨ sij.acroni.si





#### TECHNICAL DATA SHEET

	Tensile properties*			
Thickness [mm]	R <sub>p0.2</sub> [MPa] min.	R <sub>m</sub> [MPa] min.	A <sub>5.65</sub> [%] min.	
6–25	1350	1700	7	

\* For transverse tensile flat test pieces.

	Impact toughness*				
Thickness [mm]	Testing direction	Temperature [°C]	KV <sub>2</sub> [J] min.		
6–25	transverse	-20	20		

\* Measured on standard specimen 10 x 10 x 55 mm. The specified minimum value is the average of 3 tests. One individual value may be below the minimum average value specified, provided that it is not less than 70 % of that value. For plate thickness below 12 mm, subsize specimens shall be used. The minimum values of subsize specimens shall be reduced in direct proportion to the cross-sectional area of the test piece.

## DELIVERY CONDITION

• Hot-rolled quarto plates in quenched and tempered condition.

## DIMENSIONS

Thickness	Width	Length
[mm]	[mm] max.	[mm] max.
6–25	2000	12500

Plates can only be delivered with trimmed edges.

## SURFACE CONDITION

- Sandblasted
- Sandblasted and anti-corrosion painted\*

\* Thickness of the coating is 20–60  $\mu$ m.

### **INSPECTION DOCUMENTS**

The type of document shall be agreed upon at the time of enquiry and order. A test certificate according to EN 10204/3.1 is issued mandatory.

acroni

The information and data in this product data sheet are intended for informative purpose only and may be revised at any time without notice. Presented typical properties of the materials are described only to help readers make their own evaluations and decisions. They are not guaranteed.

△ SIJ ACRONI d.o.o.

Cesta Borisa Kidriča 44,

- senice, Slovenija, EU 🛛 🗹 u
- C +386 4 58 41 000

➡ +586 4 58 41 005
➡ uprava@acroni.s
① sij.acroni.si