



## SIHARD R246 Steel

### Designation by Standards

Brand Name	Ravne	Mat. No.	DIN	EN	AISI/SAE
SIHARD R246	OTV1C	-	-	-	-

### Chemical Composition (in weight %)

C	Si	Mn	Cr	Mo	Ni	V	W	Others
0.90	0.50	0.60	3.00	0.50	0.30	-	-	-

### Description

Low alloyed cold working tool steel.

### Applications

Steel for cold working rolls. For backup rolls, non-ferrous 2 and 4 high roll mills.

### Physical properties (average values) at ambient temperature

Please ask.

### Soft Annealing

Please ask.

### Stress Relieving

Please ask.

### Hardening

Please ask.

### Tempering

Please ask.

### Forging

Hot forming temperature: 1100-850°C.

### Machinability

No data.

Forms manufactured: Please see the [Dimensional Sales Program](#).

### Disclaimer

The information and data presented herein are typical or average values and are not a guarantee of maximum or minimum values. Applications specifically suggested for material described herein are made solely for the purpose of illustration to enable the reader to make his own evaluation and are not intended as warranties, either express or implied, of fitness for these or other purposes. There is no representation that the recipient of this literature will receive updated editions as the become available.

Unless otherwise specified, registered trademarks are property of SIJ Metal Ravne company. Copyright 2016 by SIJ Metal Ravne d.o.o. All rights reserved. Contact our [Sales Office](#) for more information.